



iSHINE[®]

High-Solids Floor Finish



iShine is dry-bright floor finish designed for use on many floor types, especially in heavy traffic areas. Incorporating patented optically enhanced polymer technology, iShine delivers a high gloss, high clarity finish that remains glossy for longer periods of time than traditional finishes. With a unique blend of cutting edge raw materials, iShine provides maximum protection against scuff marks, water spots, black heel marks, and other traffic damage, reducing the frequency of required maintenance. Amplify the gloss, clarity and durability of your floors with iShine.



FEATURES

- 25% non-volatile solids, high-gloss, dry bright finish
- Enhanced with optical brighteners to create increased depth of gloss and improved clarity
- Designed for use in high-traffic areas
- Meets UL standards for slip resistance

BENEFITS

- Delivers a high-gloss finish with moderate maintenance
- Floor retains gloss and clarity longer between periodic polishing
- Provides maximum protection against scuff marks, water spots, and black heel marks
- High-solids formula reduces cost, time, and labor associated with periodic recoats

CERTIFICATIONS

- Classified UL

SPECIFICATION DATA

Total Solids	32%
Non-Volatile Solids	25%
pH	8.0 – 9.0
Specific Gravity @ 24°C/75°F	1.037
Stability: Shelf @ 24°C/75°F	1 year minimum
Stability: Accelerated @ 49°C/120°F	30 days minimum
Stability: Freeze/Thaw	Will withstand 3 cycles
Gardner Gloss: 1 coat	90
Gardner Gloss: 2 coats	93
Coverage	Up to 3,000 ft² per gallon

Static coefficient of friction meets or exceeds 0.5 as determined by ASTM D-2047

DIRECTIONS FOR USE

For best results, always use Spartan floor cleaners and strippers.

INITIAL APPLICATION

1. Completely strip all old wax or floor finish. Depending upon build-up, use warm or room temperature water (80°F – 120°F) and a Spartan stripper.
2. Remove all stripping solution and follow with two to three clear water rinses.
3. When flooring is old, abused, or damaged, two coats of a Spartan sealer is recommended, though iShine may be used as a self-sealing finish.
4. Apply iShine in a uniform coat. Let dry thoroughly for 30 – 40 minutes, until surface is dry to the touch.

MAINTENANCE

ROUTINE

Dust mop with Spartan's Dust Mop / Dust Cloth Treatment and damp mop with a Spartan neutral cleaner.

WEEKLY

Dust floor with Spartan's Dust Mop / Dust Cloth Treatment and damp mop with a Spartan neutral cleaner. To repair traffic areas between finish applications, use Bounce Back®, Spraybuff®, or SunSwept®. Be careful to follow the directions for use. Traffic lanes may be re-coated as necessary.

PERIODICALLY

Dust mop floor and scrub. Reapply iShine as needed.

YEARLY

Deep scrub and recoat, or completely strip, reseal if necessary, and reapply iShine.

ORDERING INFORMATION



#545504



#545505



#545555

ADDITIONAL RESOURCES

Scan the QR code to access this product's safety information and documentation.



SAFETY: For institutional and industrial use only. Be sure to read all directions, precautionary and first aid statements on product labels before using this or any other Spartan product. If questions remain, consult your employer or a physician. Safety Data Sheets for all Spartan products are available from your authorized Spartan distributor and at www.spartanchemical.com. Workplace labels are available in English, Spanish, and French.

GUARANTEE: Spartan's modern manufacturing and laboratory control ensures uniform quality. If dissatisfied with performance of product, any unused portion may be returned for credit within 12 months of the date of manufacture.