





## Mirafi<sup>®</sup> BXG11

Mirafi<sup>®</sup> BXG11 geogrid is composed of high molecular weight, high tenacity polyester multifilament yarns which are woven in tension and finished with a PVC coating. Mirafi<sup>®</sup> BXG11 geogrid is inert to biological degradation and resistant to naturally encountered chemicals, alkalis, and acids.

Mechanical Properties	Test Method	Unit	Minimum Average Roll Value	
			MD	CD
Tensile Strength (at ultimate)	ASTM D6637	lbs/ft (kN/m)	2500 (36.5)	2500 (36.5)
Tensile Strength (at 1% strain)	ASTM D6637	lbs/ft (kN/m)	375 (5.5)	375 (5.5)
Tensile Strength (at 2% strain)	ASTM D6637	lbs/ft (kN/m)	625 (9.1)	625 (9.1)
Tensile Strength (at 5% strain)	ASTM D6637	lbs/ft (kN/m)	1000 (14.6)	1000 (14.6)
Tensile Modulus (at 1% strain)	ASTM D6637	lbs/ft (kN/m)	37500 (547)	37500 (547)
UV Resistance (at 500 hours)	ASTM D4355	% strength retained	7	0

Physical Properties	Unit	Typical Value	
Percent Open Area (COE CW-02215)	%	70	
Grid Aperture Size (MD)	in (mm)	1.0 (25.4)	
Grid Aperture Size (CMD)	in (mm)	1.0 (25.4)	
Mass/Unit Area (ASTM D5261)	oz/yd² (g/m²)	9.1 (309)	
Roll Dimensions (width x length)	ft (m)	13.1 x 164 (4 x 50)	
Roll Area	yd² (m²)	239 (200)	
Estimated Roll Weight	lbs (kg)	169 (77)	

**Disclaimer:** TenCate assumes no liability for the accuracy or completeness of this information or for the ultimate use by the purchaser. TenCate disclaims any and all express, implied, or statutory standards, warranties or guarantees, including without limitation any implied warranty as to merchantability or fitness for a particular purpose or arising from a course of dealing or usage of trade as to any equipment, materials, or information furnished herewith. This document should not be construed as engineering advice.

© 2011 TenCate Geosynthetics North America Mirafi<sup>®</sup> is a registered trademark of Nicolon Corporation



