



## PRODUCT SPECIFICATIONS

Pipe Type	PVC & CPVC, Schedule 40 & 80
Cement Uses:	For use on PVC and CPVC with all appropriate Christy's Solvent Cements
Color	Purple
Body	Water Thin
Performance Specification	ASTM F-656, NSF/ANSI 14, NSF/ANSI 61, NSF/ANSI 372
Brookfield Viscosity	Water Thin
Specific Gravity	Typical 0.842 +/- 0.04
Industry Listing	 U.P. Code PW-DWV-SW
Max VOC Emissions	550 g/l per SCAQMD Rule 1168 Method 316A 
Shelf Life	3 Years
LEED Compliant	Low VOC formulation can earn credit toward the U.S. Green Building Council's LEED certification for green buildings. 

## PURPLE PRIMER

### Professional primer for PVC and CPVC

Christy's Purple Primer aids the bonding of pipe and fittings across a wide range of job site and weather conditions. Softens and prepares PVC & CPVC pipe and fittings for solvent cementing and helps the solvent cement make stronger joints.

- Professional grade, aggressive primer for use on PVC and CPVC pipe and fittings
- Aggressive formulation softens pipe & fittings prior to application of solvent cement
- Purple color enables visual confirmation that primer has been applied
- For use with all Christy's Solvent Cements, excluding ABS
- Not for use on ABS pipe and fittings
- Low VOC

### CASE PACK CONFIGURATIONS

Item #	Can Size	Cans/Cs	Can UPC
RH-PURP-QP-24	¼ Pint, 4 oz (118 ml)	24	044752600040
RH-PURP-HP-24	½ Pint, 8 oz (237 ml)	24	044752600088
RH-PURP-PT-12	Pint, 16 oz (473 ml)	12	044752600163
RH-PURP-QT-12	Quart, 32 oz (946 ml)	12	044752600323
RH-PURP-GL-6	Gallon, 128 oz (3.785 l)	6	044752601283

**SPECIAL CONSIDERATIONS:** Consult the SDS for health and safety specifics. Always use in a well-ventilated environment. Wear safety glasses and gloves at all times. DO NOT USE a dry granular calcium hypochlorite as a disinfecting material for water purification in potable water piping systems. The introduction of granules or pellets of calcium hypochlorite with PVC and CPVC solvent cements and primers (including their vapors) may result in a violent chemical reaction if a water solution is not used. It is advisable to purify lines by pumping chlorinated water into the piping system - this solution will be non-volatile. Furthermore, dry granular calcium hypochlorite should not be stored or used near solvent cements and primers.

**THIS PRODUCT IS NOT FOR USE IN A SYSTEM USING OR BEING TESTED WITH COMPRESSED AIR OR GASSES.**

T. Christy Enterprises, Inc.



655 E. Ball Rd. • Anaheim, CA 92805

Tel: (714) 507-3300 • Fax: (714) 507-3310

www.TChristy.com • 800-BLU-GLUE