

LEAD-FREE SOLDER

FOR USE IN PLUMBING AND POTABLE WATER APPLICATIONS



SILVER BEARING ALLOY LEAD-FREE

NSF 61 Certification for safe use in potable water applications

Lead-Free Tin-Copper-Silver Solder

Wide pasty range

Melting temperature: 440° F

Tensile strength: 6600 psi

ASTM B-32



WOR PROD NO	LENOX PROD NO	DESCRIPTION	WEIGHT		DIAMETER		CARTON
			LB	G	IN	MM	QTY
331762	WS15067	Silver Bearing Alloy Spool	1	454	.118	3	50
331910	WS15068	Silver Bearing Alloy Wire Spool	1/4	113	.118	3	50

97/3 LEAD-FREE

NSF 61 Certification for safe use in potable water applications

Lead-Free Tin-Copper Solder

Melts, flows and performs better than 95/5

Melting temperature: 445° F

Tensile strength: 5800 psi

ASTM B-32



WOR PROD NO	LENOX PROD NO	DESCRIPTION	WEIGHT		DIAMETER		CARTON
			LB	G	IN	MM	QTY
331761	WS15064	97/3 Wire Spool	1	454	.118	3	50
331864	WS15397	97/3 Wire Spool	1	454	.062	1.6	50
331904	WS15355	97/3 Wire Spool	1/4	113	.118	3	50
331903	WS15066	97/3 Wire Spool	1/2	227	.118	3	50

95/5 LEAD-FREE

Lead-Free Tin-Antimony Solder

Narrow pasty range

Melting temperature: 455° F

Tensile strength: 5500 psi

ASTM B-32



WOR PROD NO	LENOX PROD NO	DESCRIPTION	WEIGHT		DIAMETER		CARTON
			LB	G	IN	MM	QTY
331760	WS15018	95/5 Wire Spool	1	454	.118	3	50
331861	WS15181	95/5 Wire Spool	1	454	.093	2.4	50
331902	WS15312	95/5 Wire Spool	1/4	113	.118	3	50
331901	WS15313	95/5 Wire Spool	1/2	227	.118	3	50

Unit lot numbering ensures complete traceability