## **PVC Performance Engineered & Tested**



SPEARS® Schedule 80 PVC product designs combine years of proven experience with computer generated stress analysis to yield the optimum physical structure and performance for each fitting. Material reinforcement is uniformly placed in stress concentration areas for substantially improved pressure handling capability. Resulting products are subjected to numerous verification tests to assure obtaining the very best PVC fittings available.

## 1/4" Through 12" Availability

Spears® comprehensive line of PVC injection molded fittings and extruded pipe offers a variety of configurations in sizes 1/4" through 12". Schedule 80 fittings are manufactured to ASTM D 2467 and pipe is produced to ASTM D 1785. Spears® exclusive CL150 Flanges are produced in sizes 1/2" - 18" with ANSI B16.5 bolt patterns, plus numerous Unions, Saddles, Transition and Specialty fittings in a variety of sizes.

### **Exceptional Chemical & Corrosion Resistance**

Unlike metal, PVC fittings and pipe never rust, scale, or pit, and will provide many years of maintenance-free service and extended system life.

### **High Temperature Ratings**

PVC thermoplastic can handle fluids at service temperatures up to 140°F (60°C), allowing a wide range of process applications, including corrosive fluids.

#### **Lower Installation Costs**

Substantially lower material costs than steel alloys or lined steel, combined with lighter weight and ease of installation, can reduce installation costs by as much as 60% over conventional metal systems.

## **Higher Flow Capacity**

Smooth interior walls result in lower pressure loss and higher volume than conventional metal fittings.

## Additional Fabricated Configurations through 36"

Extra large, hard-to-find, and custom configurations are fabricated from NSF<sub>®</sub> Certified pipe. Fittings are engineered and tested to provide full pressure handling capabilities according to Spears<sup>®</sup> specifications.

## **Advanced Design Specialty Fittings**

Spears® wide range of innovative, improved products include numerous metal-to-plastic transition fittings and unions with Spears® patented special reinforced (SR) plastic threads.

#### **PVC Valves**

SPEARS® PVC Valve products are available for total system compatibility and uniformity.

### 1/8" Through 24" Industrial Pipe Availability

Spears® premium quality Industrial CPVC pipe is offered in Schedule 80 sizes 1/8" through 24". Schedule 40 CPVC pipe is also available.

## **PVC Sample Engineering Specifications**

All PVC Schedule 80 pipe and fittings shall be produced by Spears\* Manufacturing Company from PVC Type I, cell classification 12454, conforming to ASTM Standard D 1784. All PVC injection molded Schedule 80 fittings and extruded pipe shall be Certified for potable water service by NSF International. All Schedule 80 fittings shall be manufactured in strict compliance to ASTM D 2467 and Schedule 80 pipe shall be manufactured in strict compliance to ASTM D 1785. All fabricated fittings shall be produced in accordance with Spears\* General Specifications for Fabricated Fittings. All PVC flanges shall be designed and manufactured to meet CL150 bolt pattern per ANSI Standard B16.5 and rated for a maximum internal pressure of 150 psi, non-shock at 73°F.

The information contained in this publication is based on current information and Product design at the time of publication and is subject to change without notification. Our ongoing commitment to product improvement may result in some variation. No representations, guarantees or warranties of any kind are made as to its accuracy, suitability for particular applications or results to be obtained therefrom. For verification of technical data or additional information not contained herein, please contact Spears® Technical Services Department [West Coast: (818) 364-1611 — East Coast: (678) 985-1263].

## General Information

### Recommendations For Installers And Users

Plastic piping systems should be **ENGINEERED**, **INSTALLED** and **OPERATED** in accordance with **ESTABLISHED DESIGN AND ENGINEERING STANDARDS AND PROCEDURES** for plastic piping systems. Suitability for the intended service application should be determined by the installer and/ or user prior to installation of a plastic piping system. **PRIOR TO ASSEMBLY**, all piping system components should be inspected for damage or irregularities. Mating components should be checked to assure that tolerances and engagements are compatible. Do not use any components that appear irregular or do not fit properly. Contact the appropriate manufacturer of the component product in question to determine usability. Consult all applicable codes and regulations for compliance prior to installation.

Solvent Weld Connections — Use quality solvent cements and primers formulated for the intended service application, pipe size and type of joint. While the pipe and fitting materials may be compatible with the intended medium, the solvent cement may not be. Consult the manufacturers for suitability of use. Read and follow the cement and primer manufacturers' applications and cure time instructions thoroughly. Be sure to use the correct size applicator.

Threaded Connections — Use a quality grade thread sealant. WARNING: SOME PIPE JOINT COMPOUNDS OR PTFE PASTES MAY CONTAIN SUBSTANCES THAT COULD CAUSE STRESS CRACKING TO PLASTIC. Spears® Manufacturing company recommends the use of Spears® BLUE 75™ Thread Sealant which has been tested for compatibility with Spears® products. Please follow the sealant manufacturers' application/installation instructions. Choice of an appropriate thread sealant other than those listed above is at the discretion of the installer. 1 to 2 turns beyond FINGER TIGHT is generally all that is required to make a sound plastic threaded connection. Unnecessary OVERTIGHTENING will cause DAMAGE TO BOTH PIPE AND FITTING.

## **Standards and Specifications**

Molded Schedule 80 PVC products are manufactured to ASTM D 2467 for use with pipe manufactured to ASTM D 1785. Molded Schedule 80 CPVC products are manufactured to ASTM F 439 for use with pipe manufactured to ASTM F 441. Certain products carry reduced pressure handling capability and have maximum internal pressure ratings at 73°F noted.


Fabricated Schedule 80 PVC pressure fittings (part numbers ending with "F") are manufactured to Spears® specifications for use with pipe manufactured to ASTM D 1785. Schedule 80 CPVC fabricated fittings for use with pipe manufactured to ASTM F 441. See publication FAB-7, General Specifications for Standard Fabricated Fittings for additional information.


All specified Schedule 80 PVC and CPVC products are manufactured from materials certified by NSF® for use in potable water service.

"Lead Free" low lead certification – unless otherwise specified, all Spears® Schedule 80 fittings specified here-in are certified by NSF International to ANSI/NSF® Standard 61, Annex G and is in compliance with California's Health & Safety Code Section 116825 (commonly known as AB1953) and Vermont Act 193. Weighted average lead content <=0.25%. Spears® PVC and CPVC Pipe, Fittings and Valves have always been lead-free and Certified by NSF International for use in potable water systems. Spears® offers a wide range of lead-free specialty fittings and transition adapters for plumbing applications. However, certain brass threaded adapter fittings for applications that are not intended to convey water for human consumption through drinking or cooking are still produced and available.



## **ASTM STANDARD DIMENSIONS**






THICKNESS						
Nominal Pipe Size In.	Mean Outside Diameter In.	O. D. Tolerance In.	Minimum Wall Thickness In.			
1/8	0.405	± 0.004	0.095			
1/4	0.540	± 0.004	0.119			
3/8	0.675	± 0.004	0.126			
1/2	0.840	± 0.004	0.147			
3/4	1.050	± 0.004	0.154			
1	1.315	± 0.005	0.179			
1-1/4	1.660	± 0.005	0.191			
1-1/2	1.900	± 0.006	0.200			
2	2.375	± 0.006	0.218			
2-1/2	2.875	± 0.007	0.276			
3	3.500	± 0.008	0.300			
4	4.500	± 0.009	0.337			
5	5.563	± 0.010	0.375			
6	6.625	± 0.011	0.432			
8	8.625	± 0.015	0.500			
10	10.750	± 0.015	0.593			
12	12.750	± 0.015	0.687			

#### SCHEDULE 80 SOCKET DIMENSIONS ASTM D 2467



		Diameter		Socket	
Nominal Size In.	Entrance A	Bottom B	Tolerance A	Length Minimum C	
1/8	0.417	0.401	± 0.004	0.500	
1/4	0.552	0.536	± 0.004	0.625	
3/8	0.687	0.671	± 0.004	0.750	
1/2	0.848	0.836	± 0.004	0.875	
3/4	1.058	1.046	± 0.004	1.000	
1	1.325	1.310	± 0.005	1.125	
1-1/4	1.670	1.655	± 0.005	1.250	
1-1/2	1.912	1.894	± 0.006	1.375	
2	2.387	2.369	± 0.006	1.500	
2-1/2	2.889	2.868	± 0.007	1.750	
3	3.516	3.492	± 0.008	1.875	
4	4.518	4.491	± 0.009	2.250	
5	5.583	5.553	± 0.010	2.625	
6	6.647	6.614	± 0.011	3.000	
8	8.655	8.610	± 0.015	4.000	
10	10.780	10.735	± 0.015	5.000	
12	12.780	12.735	± 0.015	6.000	

### AMERICAN NATIONAL STANDARD TAPER PIPE THREADS (NPT) ANSI B1 .20.1 ASTM F 1498



' '					
Threads Per Inch	Effective Thread Length L	Pitch Of Thread P			
27	0.2639	0.03704			
18	0.4018	0.05556			
18	0.4078	0.05556			
14	0.5337	0.07143			
14	0.5457	0.07143			
11-1/2	0.6828	0.08696			
11-1/2	0.7068	0.08696			
11-1/2	0.7235	0.08696			
11-1/2	0.7565	0.08696			
8	1.1375	0.12500			
8	1.2000	0.12500			
8	1.3000	0.12500			
8	1.4063	0.12500			
8	1.5125	0.12500			
8	1.7125	0.12500			
	Per Inch  27  18  18  14  14  11-1/2  11-1/2  11-1/2  8  8  8  8	Threads Per Inch         Thread Length L           27         0.2639           18         0.4018           18         0.4078           14         0.5337           14         0.5457           11-1/2         0.6828           11-1/2         0.7068           11-1/2         0.7565           8         1.1375           8         1.2000           8         1.3000           8         1.5125			

## STANDARD COMPARISONS

SPEARS® IPS-to-Metric transition unions are listed by nominal size. The chart below compares nominal and actual\* pipe O.D. for each size according to the designated standard.

	JIS K6741 DIN 8062 (mm) (mm)		ASTM D1785 (in.)		NPT—ANSI B1.20.1** Tapered Thread		BSP—BS21,DIN 2999,ISO 7/1 Thread		
Nominal	Actual*	O.D.	Actual*	Nominal	Actual*	Designation	Threads/in.	Designation	Threads/25.4mm
16	22	15	20	1/2	.840	1/2	14	1/2	14
20	26	20	25	3/4	1.050	3/4	14	3/4	14
25	32	25	32	1	1.315	1	11.5	1	11
30	38	38	40	1-1/4	1.660	1-1/4	11.5	1-1/4	11
40	48	40	50	1-1/2	1.900	1-1/2	11.5	1-1/2	11
50	60	50	63	2	2.375	2	11.5	2	11
75	89	80	90	3	3.500	3	8	3	11
100	114	100	110	4	4.500	4	8	4	11

<sup>\*</sup>Specified dimension, certain tolerances apply

<sup>\*\*</sup>NPT and BSP have different thread angles and not compatible.



## Injection Molded Dimensions Referencesces:

- G = (LAYING LENGTH) intersection of center lines to bottom of socket/thread; 90° elbows, tees, crosses; ± 1/32 inch.


  H = Intersection of center lines to face of fitting; 90° elbow tees,
- crosses; ± 1/32 inch.
- J = Intersection of center lines to bottom of socket/thread; 45° elbows; ± 1/32 inch
- L = Overall length of fittings; ± 1/16 inch.
- H = Outside diameter of socket/thread hub; ± 1/16 inch.
- N = Socket bottom to socket bottom; couplings; ± 1/16 inch W = Height of cap; ± 1/16 inch.


#### **Fabricated Dimension References:**


- G = (LAYING LENGTH) intersection of center lines to bottom of socket/thread; 90° elbows, tees, crosses ± 1/4 inch; 14" & larger ± 1/2 inch.
- H = Intersection of center lines to face of fitting; 90° elbows ± 1/4 inch, 14" & larger ± 3/4 inch; wyes ± 1/2 inch; tees, crosses
- ± 1/4 inch; 14" & larger ± 1/2 inch.


  J = Intersection of center lines to bottom of socket/thread; 45° elbows; ± 1/4 inch; 14" & larger ± 1/2 inch.
- L = Overall length of fittings; ± 1/2 inch; 14" & larger ± 1 inch; wyes ± 1 inch.
- M = Outside diameter of socket/thread hub; ± 1/4 inch.
- N = Socket bottom to socket bottom; couplings; ± 1/2
- W = Height of cap; ± 1/4 inch.

## **Typical Fabricated Dimension References**











Socket x Socket x Socket



Part N	umber	Size	Cizo	G	C1		111		N/	Approx.	Wt. (Lbs.)
PVC	CPVC		G	G1	Н	H1	L	M	PVC	CPVC	
801-002	801-002C	1/4	5/16	5/16	31/32	31/32	1-15/16	27/32	.04	.04	
801-003	801-003C	3/8	15/32	15/32	1-1/4	1-1/4	2-1/2	31/32	.06	.06	
801-005	801-005C	1/2	17/32	17/32	1-15/32	1-15/32	2-15/16	1-3/16	.11	.11	
801-007	801-007C	3/4	21/32	21/32	1-11/16	1-11/16	3-13/32	1-13/32	.16	.18	
801-010		1	7/8	7/8	2	2	4	1-3/4	.27		
	801-010C	1	27/32	27/32	2	2	3-31/32	1-23/32		.29	
801-012	801-012C	1-1/4	1-1/32	1-1/32	2-9/32	2-9/32	4-19/32	2-3/32	.39	.40	
801-015	801-015C	1-1/2	1-3/16	1-3/16	2-9/32	2-9/32	5-1/8	2-3/8	.52	.57	
801-020	801-020C	2	1-11/32	1-11/32	2-15/16	2-15/16	5-27/32	2-7/8	.80	.85	
801-025		2-1/2	1-3/4	1-3/4	3-1/2	3-1/2	7-1/32	3-15/32	1.46		
	801-025C	2-1/2	1-23/32	1-23/32	3-1/2	3-1/2	7	3-15/32		1.62	
801-030	801-030C	3	2-3/32	2-3/32	3-31/32	3-31/32	7-15/16	4-3/16	2.16	2.43	
801-040	801-040C	4	2-1/2	2-1/2	4-3/4	4-3/4	9-1/2	5-1/4	3.52	3.72	



## **REDUCER BUSHING** (continued) Flush Style Spigot x Fipt



Part Number		C'-	.		Approx. Wt. (Lbs.)		
PVC	CPVC	Size	L	N	PVC	CPVC	
838-207	838-207C	1-1/2x1/4	1-9/16	1-3/16	.13	.14	
838-209	838-209C	1-1/2x1/2	1-11/16	31/32	.17	.17	
838-210	838-210C	1-1/2x3/4	1-9/16	27/32	.13	.18	
838-211	838-211C	1-1/2x1	1-23/32	13/16	.14	.16	
838-212	838-212C	1-1/2x1-1/4	1-1/2	9/16	.07	.10	
838-247	838-247C	2x1/2	1-29/32	1-5/32	.25	.27	
838-248	838-248C	2x3/4	1-7/8	1-5/32	.26	.27	
838-249	838-249C	2x1	1-29/32	1	.25	.27	
838-250	838-250C	2x1-1/4	1-19/32	21/32	.18	.25	
838-251	838-251C	2x1-1/2	1-9/16	5/8	.14	.20	
838-287	838-287C	2-1/2x1/2	2-3/8	1-21/32	.41	.46	
838-288	838-288C	2-1/2x3/4	2-7/16	1-5/8	.45	.48	
838-289	838-289C	2-1/2x1	2-13/32	1-13/32	.45	.48	
838-290	838-290C	2-1/2x1-1/4	2-13/32	1-3/8	.42	.45	
838-291	838-291C	2-1/2x1-1/2	2-3/8	1-13/32	.47	.50	
838-292	838-292C	2-1/2x2	2-1/16	1-1/16	.25	.33	
838-334	838-334C	3x3/4	2-9/32	1-1/2	.57	.63	
838-335	838-335C	3x1	2-9/32	1-11/32	.58	.63	
838-336	838-336C	3x1-1/4	2-1/4	1-3/8	.57	.61	
838-337	838-337C	3x1-1/2	2-1/4	1-5/8	.59	.62	
838-338	838-338C	3x2	2-3/16	1-7/32	.63	.58	
838-339	838-339C	3x2-1/2	2-3/8	3/4	.46	.50	
838-419		4x1-1/2	3-3/16	2-5/16	1.44		
838-420	838-420C	4x2	2-11/16	1-21/32	1.10	1.20	
838-421	838-421C	4x2-1/2	2-21/32	1-1/16	1.08	1.15	
838-422	838-422C	4x3	2-5/8	1	.86	.85	
838-528	838-528C	6x2	3-17/32	2-1/2	2.92	3.04	
838-530	838-530C	6x3	3-17/32	2-1/8	2.98	3.14	
838-532	838-532C	6x4	3-17/32	2-1/32	2.54	2.68	