

PVC SCHEDULE 40 FITTINGS

40-2-0604

Performance Engineered & Tested



SPEARS[®] Schedule 40 PVC fitting designs combine years of proven experience with computer generated stress analysis to yield the optimum physical structure and performance for each fitting. Material reinforcement is uniformly placed in stress concentration areas for substantially improved pressure handling capability. Resulting products are subjected to numerous verification tests to assure the very best PVC fittings available.

Full 1/4" Through 12" Availability

Spears[®] comprehensive line of PVC fittings offers a variety of injection molded configurations in Schedule 40 sizes 1/4" through 12" conforming to ASTM D 2466.

Exceptional Chemical & Corrosion Resistance

Unlike metal, PVC fittings never rust, scale, or pit, and will provide many years of maintenance-free service and extended system life.

High Temperature Ratings

PVC thermoplastic can handle fluids at service temperatures up to 140°F (60°C), allowing a wide range of process applications, including corrosive fluids.

Lower Installation Costs

Substantially lower material costs than steel alloys or lined steel, combined with lighter weight and ease of installation, can reduce installation costs by as much as 60% over conventional metal systems.

Sample Engineering Specifications

All PVC Schedule 40 fittings shall be produced by Spears[®] Manufacturing Company from PVC Type I cell classification 12454, conforming to ASTM D 1784. All injection molded PVC Schedule 40 fittings shall be Certified for potable water service by NSF International and manufactured in strict compliance to ASTM D 2466. All fabricated fittings shall be produced in accordance with Spears[®] General Specifications for Fabricated Fittings.

Higher Flow Capacity

Smooth interior walls result in lower pressure loss and higher volume than conventional metal fittings.

Additional Fabricated Configurations through 36"

Extra large, hard-to-find, and custom configurations are fabricated from NSF Certified pipe. Fittings are engineered and tested to provide full pressure handling capabilities according to Spears[®] specifications.

PVC Valves

SPEARS[®] PVC Valve products are available for total system compatibility and uniformity; see SPEARS[®] THERMOPLASTIC VALVES PRODUCT GUIDE & ENGINEERING SPECIFICATIONS (V-4).

Advanced Design Specialty Fittings

Spears[®] wide range of innovative, improved products include numerous metal-to-plastic transition fittings and unions with Spears[®] patented special reinforced (SR) plastic threads.



PROGRESSIVE PRODUCTS FROM SPEARS® INNOVATION & TECHNOLOGY Visit our web site: www.spearsmfg.com

PVC WHITE SCHEDULE 40 FITTINGS UNIONS & SADDLES



UNION Socket x Sock	et w/O-ring Seal	l			Pressi	ure Rating 150 ps	i @ 73°F
Part N	umber						
w/O-ring Seal		Size	L	М	N	Nut	Approx. Wt. (Lbs.)
BUNA-N	EPDM					0.D.	
457-005	497-005	1/2	1-27/32	1-3/32	11/32	1-23/32	.08
457-007	497-007	3/4	2-3/16	1-5/16	11/32	1-31/32	.12
457-010	497-010	1	2-7/16	1-5/8	11/32	2-3/8	.18
457-012	497-012	1-1/4	2-29/32	1-31/32	13/32	2-11/16	.24
457-015	497-015	1-1/2	3-1/32	2-1/4	3/8	3-3/32	.32
457-020	497-020	2	3-9/32	2-23/32	17/32	3-5/8	.54
457-025	497-025	2-1/2	4-1/16	3-11/32	9/16	4-3/8	.85
457-030	497-030	3	4-11/32	4	11/16	5-3/32	1.26
457-040	497-040	4	4-5/8	5-1/32	19/32	6-3/16	1.78
457-060	497-060	6	6-7/8	7-9/32	13/16	8-7/8	5.22

PVC Thermoplastic Pipe Temperature Pressure De-Rating

To determine the maximum internal pressure rating at an elevated temperature, simply multiply the pipe pressure rating at 73°F by the percentage specified for the desired temperature.

System Operating	73	80	90	100	110	120	130	140
Temperature °F (°C)	(23)	(27)	(32)	(38)	(43)	(49)	(54)	(60)
PVC	100%	90%	75%	62%	50%	40%	30%	

NOTE: Valves, Unions and Specialty Products have different elevated temperature ratings than pipe.

PVC Basic Physical Properties

Properties	ASTM Test Method	PVC				
Mechanical Properties, 73°F						
Specific Gravity, g/cm ³	D 792	1.41				
Tensile Strength, psi	D 638	7,200				
Modulus of Elasticity, psi	D 638	440,000				
Compressive Strength, psi	D 695	9,000				
Flexural Strength, psi	D 790	13,200				
Izod Impact, notched, ft-lb/in	D 256	.65				
Thermal Properties						
Heat Deflection Temperature, °F at 66 psi	D 648	165				
Thermal Conductivity, BTU/hr/sq ft/°F/in	C 177	1.2				
Coefficient of Linear Expansion, in/in/°F	D 696	3.1 X 10⁵				
Flammability						
Limiting Oxygen Index, %	D 2863	43				
UL 94 rating	94V-0					
Other Properties						
Water Absorption, % 24 hr.	D 570	.05				
Industry Standard Color	White / Dark Gray					
ASTM Cell Classification	D 1784	12454				
NSF Potable Water Approved	Yes					

PVC Chemical Resistance

PVC is generally inert to most mineral acids, bases, salts and paraffinic hydrocarbon solutions. For more information on PVC chemical resistance refer to the Chemical Resistance of Rigid Vinyls Based on Immersion Test, published by the GEON[®] Company.

NOT FOR USE WITH COMPRESSED AIR OR GAS

Spears[®] Manufacturing Company DOES NOT RECOMMEND the use of thermoplastic piping products for systems to transport or store compressed air or gases, or the testing of thermoplastic piping systems with compressed air or gases in above and below ground locations. The use of our product in compressed air or gas systems automatically voids any warranty for such products, and its use against our recommendation is entirely the responsibility and liability of the installer.

WARNING: DO NOT USE COMPRESSED AIR OR GAS TO TEST ANY PVC OR CPVC THERMOPLASTIC PIPING PRODUCT OR SYSTEM, AND DO NOT USE DEVICES PROPELLED BY COMPRESSED AIR OR GAS TO CLEAR SYSTEMS. THESE PRACTICES MAY RESULT IN EXPLOSIVE FRAGMENTATION OF SYSTEM PIPING COMPONENTS CAUSING SERIOUS OR FATAL BODILY INJURY.



SPEARS® MANUFACTURING COMPANY • CORPORATE OFFICE

15853 Olden St., Sylmar, CA 91342 • PO Box 9203, Sylmar, CA 91392 (818) 364-1611 • www.spearsmfg.com



MIDWEST

1 Gateway Ct . Suite A

Fax (630) 759-7515

15853 Olden St.

Bolingbrook (Chicago), IL 60440

(630) 759-7529 • (800) 662-6330

INTERNATIONAL SALES

Sylmar (Los Angeles), CA 91342

(818) 364-1611 • Fax (818) 898-3774

PACIFIC SOUTHWEST 15860 Olden St. Sylmar (Los Angeles), CA 91342 (818) 364-1611 • (800) 862-1499

(818) 364-1611 • (800) 862-1499 Fax (818) 367-3014

NORTHWEST

4103 C St. NE Suite 200 Auburn (Seattle), WA 98002 (253) 939-4433 • (800) 347-7327 Fax (253) 939-7557 ROCKY MOUNTAIN 4880 Florence St. Denver, CO 80238 (303) 371-9430 • (800) 777-4154 Fax (303) 375-9546

SOUTH CENTRAL

4250 Patriot Dr. Suite 300 Grapevine (Dallas), TX 76051-2317 (972) 691-4003 • (800) 441-1437 Fax (972) 691-4404

UTAH

5395 West 1520 South Salt Lake City, UT 84104 (303) 371-9430 • (800) 777-4154 Fax (303) 375-9546

NORTHEAST

590 Industrial Dr. Suite 100 Lewisberry (Harrisburg), PA 17339-9532 (717) 938-8844 • (800) 233-0275 Fax (717) 938-6547

SOUTHEAST

4205 Newpoint PI. Suite 100 Lawrenceville (Atlanta), GA 30043 (678) 985-1263 • (800) 662-6326 Fax (678) 985-5642

FLORIDA

9563 Parksouth Court Orlando, FL 32837 (407) 843-1960 • (800) 327-6390 Fax (407) 425-3563

© Copyright 2007 Spears® Manufacturing Company. All Rights Reserved. Printed in the United States of America 01/07.