Pumpable Sealer



Product Data Sheet

Features

Description

Pumpable Sealant is a one component, nondrying, permanently flexible material designed for sealing rigid and expansion joints between all combinations of wood, glass, metals, and masonry surfaces without the need or requirement of a primer.

Pumpable is used in 5 gallon pail/55 gallon drum to provide a moisture and vapor tight seal to exclude water and dust from any given area under atmospheric pressure.

Non-Corrosive: No pitting or corrosion after 7 days aging of the sealant on metals that were in water at 160° F; test was preceded by a 24 hour cure at 77° F.

Wt. Per Gallon: 12 to 13 pounds - ASTM D71-72.

Water Immersion: no affect after three weeks in water at

120° F.

Bubble formation: Will not exceed 25% of surface after 72 hours at 160° F.

nours at 160° F.

Toxicity: Non-toxic under normal use - do not take

internally.

Composition: Butyl rubber, resins, inert pigments.

Adhesion: Adheres to oily metal surfaces, painted and

unpainted galvanized steel or aluminum.

Flexibility: No cracking, separation or loss of adhesion of a $3/8^{\prime\prime}$ diameter bead on galvanized steel when bent at

-60° F over a 1/2" mandrel

Percent Shrinkage: 15% maximum

Standard Construction

Properties	Test Method	Value
Composition		Butyl rubber, resins, inert pigments
Color	ASTM D1729-69	Gray
Wt. Per Gallon	ASTM d71-72	12 TO 13 POUNDS
Percent Solids	ASTM C771-74	Theoretically 90%
Flashpoint	ASTM D93-79	Greater than 102° F. Non-red label
Moisture Vapor Transmission (MVT)	ASTM-E-96	Less than 1.0 gram per day per M, 20 mil.
Temperature tolerance range	ASTM-D-2202	Maximum slump of 3/16" at 210° F
Temperature usage range	0°F to +100° F	Recommended
Weatherometer Test		After 1,000 hours, no significant change
S1 Sunlamp Exposure		After 1,000 hours, no apparent change
Water Immersion		No affect after being in water for 3 weeks @ 120° F

Packaging

5 Gallon Pail 55 Gallon Drum

Guarantee

All Elgen products are guaranteed by Elgen Manufacturing against defective material.

Elgen Manufacturing

10 Railroad Ave, Closter NJ 07624 Tel: 800.503.9805 :: Fax: 201.964.9030 info@elgenmfg.com :: www.elgenmfg.com