



## MRO COLD GALV PRIMER

#16-1445

A cold galvanizing primer that contains 93% Type I inorganic zinc in the dried paint film. Resists oxidation, and the galvanizing protection continues even if scratched. Can be topcoated for maximum durability.

### Suggested Uses:

Touch up galvanized metal  
Zinc protection for iron  
Galvanize metal structures

Use on projects that require  
90% minimum zinc content

### Packaging:

UPC Code	043281006828
Cans per case	6
Shipping weight per case	7.5 lbs.
Container	16 fluid ounce can
Label weight	15 ounces (425 grams)
Shipping Classification	Consumer Commodity ORM-D, UN 1950
Hazard Class	2.1

### Properties:

Coverage	Up to 15 square feet
Cleanup	Paint or lacquer thinner
Flash point	-4 F
Specific Gravity	0.87
Solids Content	52%
% zinc in dried paint film	93.5%
MIR value	1.18, cannot exceed 1.25
HAPs content	17%
Storage Temperature	40-100F
Application Temperature	50-90F
Durability	Very Good
Abrasion Resistance	Very Good
Heat Resistance	350F
Resin System	Modified Epoxy
Shelf life	Guaranteed for 2 years
Food contact rating Category 21:	Acceptable

### Dry Time\*:

To touch	5 minutes
To topcoat	20 minutes

\*At 72F, 50% humidity,  
1.5 mil thickness

\*\*Curing/Recoat time is extended with  
multiple coats and excessively thick coats\*\*

**Gloss\*:** Flat, <15

\*as measured on a 60 degree gloss meter

### Meets or exceeds the following performance requirements:

ASTM A780  
MIL-P-26915D  
MIL-P-46105  
DOD-P-21035B  
SSPC-Paint 20