



**Canfield Technologies, Inc.**

# SilverSafe

*Professional Grade*

Made in U.S.A. 



## TECHNICAL DATA

Melting Temperature:	410 -424° F
Tensile Strength:	7130
Shear Strength (psi):	5970
Brinell Hardness:	15.1

**Narrow Pasty Range Allows Solder to Set Up Quick  
Excellent Working Quality**

**Meets All Local, State & Federal Specifications for Use on Potable Water Systems**

**Certified to ANSI/NSF61  
Meets AB1953  
UPC Approved  
Meets ASTM B32**



1 S. Crossman Road, Sayreville, NJ 08872  
Tel: 732-316-2100 • Fax: 732-316-2177 • Toll Free: 800-526-4577  
[www.solders.com](http://www.solders.com)

SS0512CS