

ANVIL 9200 SERIES GATOR GRIP



ORDERING:

- Available in 1 gallon cans and 5 gallon buckets.
- Coverage Rate: 300 sq. ft. per gallon, per coat depending on the type of surface and porosity.

DESCRIPTION:

- Technologically advanced formula which combines the durability of an epoxy fortified anti-skid coating and primer in a single component product.
- When applied to a properly prepared surface is highly resistant to the effects of hot automobile tires and delivers a solid color anti-skid finish.
- Formulated for use on interior and exterior painted or unpainted concrete surfaces such as garage floors, driveways, patios, walkways, decks, basements, shop floors, pool decks and sidewalks.
- Also, formulated to be highly resistant to automotive chemicals, oil, grease and gasoline. Its durable acrylic/ epoxy/primer formula also resists fading, scuffing, cracking, peeling and blistering.

PRODUCT	NO	SIZE	UPC	Case Size (L x W x H)	Case Qty.	Pallet Qty.	
SEE PRODUCT DETAILS ON PAGE 3							

STORAGE & HANDLING:

- Warning! If you scrape, sand, or remove old paint, you may release lead dust. Lead is toxic. Exposure to lead dust can cause serious illness, such as brain damage. Especially in children. Pregnant women should also avoid exposure. Wear an NIOSH-approved respirator to control lead exposure.
- To avoid breathing vapors and spray mist, open windows and doors or use other means to ensure fresh air entry during application and drying.
- If you experience eye watering, headaches or dizziness, increase fresh air.
- A dust mask does not provide protection against vapors.
- Use only with adequate ventilation.
- · Wash thoroughly after handling.
- Clean up carefully with a HEPA vacuum and a wet mop.
- KEEP AWAY FROM CHILDREN.
- KEEP FROM FREEZING
- FIRST AID: In case of skin contact, wash thoroughly with soap and water. If any product remains, gently rub petroleum jelly, vegetable or mineral/baby oil onto skin, then wash again with soap and water. Repeated applications may be needed. Remove contaminated clothing. For eye contact, flush immediately with large amounts of water, for at least 15 minutes. If swallowed, get medical attention immediately. If inhalation causes physical discomfort, move to fresh air. If discomfort persists or any breathing difficulty occurs, get medical help.

PRECAUTIONS:

- Before you start, find out how to protect yourself and your family by contacting the National Lead Information Hotline at 1-800-424-LEAD or log on to www.epa.gov/lead.
- Warning! Irritant! Harmful if swallowed, when tinted, contains ethylene glycol which can cause severe kidney damage when ingested and has been shown to cause birth defects in laboratory animals.
- Intentional misuse by deliberately concentrating and inhaling the contents may be harmful or fatal.
- May cause eye, nose and throat irritation.
- · Do not take internally.
- Do not breathe vapors or spray mist.
- Avoid contact with skin and eyes. Wear eye protection and protective clothing.
- For emergency information call (800) 545-2643.
- For additional safety information, refer to the Safety Data Sheet for this product.
- If properly used, a respirator may offer additional protection. Obtain professional advice before using.
- · Close container after each use.



WARNING: This product can expose you to chemicals including Titanium Dioxide, which is known to the State of California to cause cancer. For more information go to www.P65Warnings.ca.gov

ANVIL 9200 SERIES GATOR GRIP

PROPERTIES	
Weight per Gallon	10.16 lbs.
Color(s)	See chart below
Gloss	Low Sheen
VOC Content	48.8 Grams per Liter (cal.)
Viscosity	78 KU @ 75° F
Solid Content by Weight	43.7%
Solid Content by Volume	31.5%
Resin	Cross-linking Acrylic
Flash Point	None
Dry Time @ 70°F & 50% RH Drying times are influenced by ambient temperature and relative humidity.	To Touch: 1/2 to 1 Hour To Recoat: 1 to 2 Hours Foot Traffic: 3 to 4 Hours Vehicle Traffic: 72 Hours

COLORS:

Dover Grey	Brick Red	Deck Grey	Pacific Fog	Desert Beige
9201	9202	9203	9214	9206
Terra Cotta	White Tint Base	Intermediate Tint Base	Accent Tint Base	
9208	9220	9221	9222	

DIRECTIONS FOR USE AND SURFACE PREPARATION

- Concrete should be at least 45 days old to reduce the possibility of the occurrence of efflorescence.
- Do not apply to concrete where hydrostatic pressure is present or over 3 lbs. of moisture per 1000 sq. ft. ASTM F1869-04.
- Not intended for use over wood or areas of standing water. Do not apply over two- part polyurethane or epoxy coatings. Check for a high pH, ASTM D4262 specification.
- Proper preparation will ensure maximum adhesion, durability, and uniform coloration, ASTM D4258-83 Specification.
- The surface must be clean and free of all wax, grease, oil, dirt, acid, mildew, release agents and all other surface contaminants.
- Failure to remove grease, oil, soap or other contamination will interfere with adhesion of the concrete coating.

- To clean a previously stained or painted surface, we recommend using Anvil 1450 Cleaner & Etcher. Remove loose or peeling paint. Rinse thoroughly with a power washer.
- Glossy painted surfaces must be dulled by sanding or abrading. Unpainted concrete surfaces should be mechanically abraded or acid etched before staining, ASTM D4260 Specification. Use Anvil 1450 Cleaner & Etcher by following label directions.
- Rinse area thoroughly with a power washer and allow to COMPLETELY dry before applying GatorGrip.
- A properly etched surface will have the feel of 120 grit sandpaper. Extremely hard, glossy or alkaline concrete may require stronger acid solutions or repeated etching with Anvil 1450 Cleaner & Etcher.

APPLICATION

- Coverage is approximately 200 sq. ft. per coat over coarse concrete and 400 sq. ft. per gallon, per coat, over smooth concrete.
- Do not dilute. Do not apply if the threat of rain is imminent or if the air/surface temperature is expected to be below 50°F within the first 24 hours of application.
- Do not apply in extreme heat of day or in direct hot sunlight. Allow 3 days (72 hours) before allowing vehicle traffic on the coating.
- Hand stir product thoroughly before application.
- To ensure uniform color, all containers of the same color must be intermixed and stirred periodically during application.
- Apply in thin multiple coats by brush, roller or spray. Avoid heavy application resulting in runs, ponding, flood coating or puddling.
- Allow two hours drying time between coats. Apply each coat at right angles to the first coat. If relative humidity is high (> 80%), allow an extra period of drying time between coats.
- Self-priming in two thin coats depending on the surface porosity being coated to achieve color uniformity.
- Full cure in 21 days. We recommend that a parked car stand on cardboard until full cure.

CLEANUP:

Soap and water.

ANVIL 9200 SERIES GATOR GRIP

PRODUCT	NO	SIZE	UPC	Case Size (L x W x H)	Case Qty.	Pallet Qty.
9201 GATOR GRIP 1G	920101	1G	760428920112	14" x 14" x 8"	4	54 Cases
9201 GATOR GRIP 5 G	920105	5G	760428920150	12" x 12" x 15"	1	36 Cases
9202 GATOR GRIP 1 G	920201	1G	760428920211	14" x 14" x 8"	4	54 Cases
9202 GATOR GRIP 5 G	920205	5G	760428920259	12" x 12" x 15"	1	36 Cases
9203 GATOR GRIP 1 G	920301	1G	760428920310	14" x 14" x 8"	4	54 Cases
9203 GATOR GRIP 5 G	920305	5G	760428920358	12" x 12" x 15"	1	36 Cases
9206 GATOR GRIP 1 G	920601	1G	760428920617	14" x 14" x 8"	4	54 Cases
9206 GATOR GRIP 5 G	920605	5G	760428920655	12" x 12" x 15"	1	36 Cases
9208 GATOR GRIP 1 G	920801	1G	760428920815	14" x 14" x 8"	4	54 Cases
9208 GATOR GRIP 5 G	920805	5G	760428920853	12" x 12" x 15"	1	36 Cases
9214 GATOR GRIP 1 G	921401	1G	760428921416	14" x 14" x 8"	4	54 Cases
9214 GATOR GRIP 5 G	921405	5G	760428921454	12" x 12" x 15"	1	36 Cases
9220 GATOR GRIP WTB	922001	1G	760428922017	14" x 14" x 8"	4	54 Cases
9220 GATOR GRIP WTB	922005	5G	760428922055	12" x 12" x 15"	1	36 Cases
9221 GATOR GRIP INT TB 1 G	922101	1G	760428922116	14" x 14" x 8"	4	54 Cases
9221 GATOR GRIP INT TB 5 G	922105	5G	760428922154	12" x 12" x 15"	1	36 Cases
9222 GATOR GRIP ACC TB 1 G	922201	1G	760428922215	14" x 14" x 8"	4	54 Cases
9222 GATOR GRIP ACC TB 5 G	922205	5G	760428922253	12" x 12" x 15"	1	36 Cases

FOR BEST RESULTS:



Clean and Etch



Apply 2 Coats



Clean Immediately with Warm Soapy Water.