



**Mueller Streamline Co. Headquarters**  
 150 Schilling Blvd  
 Suite 201  
 Collierville, Tennessee 38017  
 United States  
 Phone: 901 753 3200

**Mueller Streamline Co. International**  
 525 Okeechobee Blvd  
 Suite 860  
 West Palm Beach, FL 33401  
 United States  
 Phone: 561 273 8300

## ITEM # X 04032, REDUCING TEE, C X C X C, 7/8" X 7/8" X 3/4"

Streamline® XHP™ Copper-Iron Fittings for use in refrigeration applications. Available sizes ranging from 3/8" to 2-1/8" for continuous 130 BAR / 1885 PSI pressure ratings at 120°C / 250°F.



[Specifications](#) | [Dimensions](#) | [Details](#)

### Specifications

Weight	0.17 lb
Material <sup>1</sup>	COPPER-IRON
Operating Temperature [Max]	250 °F
Operating Pressure [Max]	1885 psi
End Type	Cup (Braze)
End Size	7/8 in

Second End Type	Cup (Braze)
Second End Size	7/8 in
Third End Type	Cup (Braze)
Third End Size	3/4 in
Standards	Copper-iron (CuFe2P) UNS C19400 130 BAR / 1,885 PSI 120°C / 250°F

## Dimensions

Overall Length	2.18 in
Overall Height	1.59 in
Overall Width	1.00 in
X	0.47 in
X1	0.47 in
Y	0.55 in

## Details

Qty Pcs / Bag	5
Master Qty Pcs / Box	100
Mueller Description	7/8 X 7/8 X 3/4 OD TEE

### Key Specifications

Streamline® XHP™ Copper Fittings is third party verified through Underwriters Laboratories for max operating temperature of 250° F (120° C) and continuous operating pressure of 1740 psi (120 Bar).

Streamline® XHP™ copper material was developed for use with high pressure refrigerants. Compared to conventional pure copper Cu-DHP (99.9% Cu; UNS C12200), Streamline® XHP™ material is a CuFe2P alloy (2% iron; UNS C19400). This material's wettability is

## Installation

comparable to that of Cu-DHP. Streamline® XHP™ is not subject to any restrictions for the selection of brazing alloy. Commonly used brazing filler metal types such as BCup Alloy (may contain 0%-30% Silver – Ag) or Bag Alloy (may contain anywhere between 24% and 93% Silver – Ag) can be used. The brazing alloy chosen must be clarified with the brazing alloy supplier for each specific application. The selection of brazing alloy may depend on a few factors: applicable codes, OEM specifications, vibration, and operating temperatures.

<sup>1</sup> Streamline® XHP™ Copper Fittings shall be made from material in compliance with UNS C19400 grade of copper.