

## Mueller Streamline Co. Headquarters

150 Schilling Blvd Suite 201

Collierville, Tennessee 38017

**United States** 

Phone: 901 753 3200

## Mueller Streamline Co. International

525 Okeechobee Blvd

Suite 860

West Palm Beach, FL 33401

**United States** 

Phone: 561 273 8300

## ITEM # X 04034, REDUCING TEE, C X C X C, 7/8" X 7/8" X 1/2"

Streamline® XHP $^{TM}$  Copper-Iron Fittings for use in refrigeration applications. Available sizes ranging from 3/8" to 2-1/8" for continuous 130 BAR / 1885 PSI pressure ratings at 120°C / 250°F.



## <u>Specifications | Dimensions | Details</u>

Specifications –					
	Weight	0.17 lb			
	Material <sup>1</sup>	COPPER-IRON			
	Operating Temperature [Max]	250 °F			
	Operating Pressure [Max]	1885 psi			
	End Type	Cup (Braze)			
	End Size	7/8 in			

Second End Type	Cup (Braze)
Second End Size	7/8 in
Third End Type	Cup (Braze)
Third End Size	1/2 in
Standards	Copper-iron (CuFe2P) UNS C19400 130 BAR / 1,885 PSI 120°C / 250°F

Dir	Dimensions –				
	Overall Length	2.10 in			
	Overall Height	1.47 in			
	Overall Width	1.00 in			
	X	0.35 in			
	X1	0.35 in			
	Υ	0.51 in			

Det	Details				
	Qty Pcs / Bag	5			
	Master Qty Pcs / Box	100			
	Mueller Description	7/8 X 7/8 X 1/2 OD TEE			
	Key Specifications	Streamline® XHP <sup>TM</sup> Copper Fittings is third party verified through Underwriters Laboratories for max operating temperature of 250° F (120° C) and continuous operating pressure of 1740 psi (120 Bar).			
		Streamline® XHP <sup>TM</sup> copper material was developed for use with high pressure refrigerants. Compared to conventional pure copper Cu-DHP (99.9% Cu; UNS C12200), Streamline® XHP <sup>TM</sup> material is a CuFe2P alloy (2% iron; UNS C19400). This material's wettability is			

Installation

comparable to that of Cu-DHP. Streamline® XHP<sup>TM</sup> is not subject to any restrictions for the selection of brazing alloy. Commonly used brazing filler metal types such as BCup Alloy (may contain 0%-30% Silver – Ag) or Bag Alloy (may contain anywhere between 24% and 93% Silver – Ag) can be used. The brazing alloy chosen must be clarified with the brazing alloy supplier for each specific application. The selection of brazing alloy may depend on a few factors: applicable codes, OEM specifications, vibration, and operating temperatures.

<sup>&</sup>lt;sup>1</sup> Streamline® XHP<sup>TM</sup> Copper Fittings shall be made from material in compliance with UNS C19400 grade of copper.