

Mueller Streamline Co. Headquarters

150 Schilling Blvd Suite 201 Collierville, Tennessee 38017 United States Phone: 901 753 3200

Mueller Streamline Co. International

525 Okeechobee Blvd Suite 860 West Palm Beach, FL 33401 United States Phone: 561 273 8300

ITEM # X 04010, REDUCING TEE, C X C X C, 5/8" X 1/2" X 1/2"

Streamline® XHPTM Copper-Iron Fittings for use in refrigeration applications. Available sizes ranging from 3/8" to 2-1/8" for continuous 130 BAR / 1885 PSI pressure ratings at 120°C / 250°F.



<u>Specifications</u> | <u>Dimensions</u> | <u>Details</u>

Specifications		-
Weight	0.07 lb	
Material ¹	COPPER-IRON	
Operating Temperature [Max]	250 °F	
Operating Pressure [Max]	1885 psi	
End Type	Cup (Braze)	
End Size	5/8 in	

7/18/2022 | Page 2 of 3

Second End Type	Cup (Braze)
Second End Size	1/2 in
Third End Type	Cup (Braze)
Third End Size	1/2 in
Standards	Copper-iron (CuFe2P) UNS C19400 130 BAR / 1,885 PSI 120°C / 250°F

Dimensions

Overall Length	1.61 in
Overall Height	1.12 in
Overall Width	0.72 in
Х	0.31 in
X1	0.31 in
Υ	0.39 in

Details

Qty Pcs / Bag	5
Master Qty Pcs / Box	100
Mueller Description	5/8 X 1/2 X 1/2 OD TEE
Key Specifications	Streamline® XHP TM Copper Fittings is third party verified through Underwriters Laboratories for max operating temperature of 250° F (120° C) and continuous operating pressure of 1740 psi (120 Bar).
	Streamline® XHP TM copper material was developed for use with high pressure refrigerants. Compared to conventional pure copper Cu-DHP (99.9% Cu; UNS C12200), Streamline® XHP TM material is a CuFe2P alloy (2% iron; UNS C19400). This material's wettability is

Installation

comparable to that of Cu-DHP. Streamline® XHPTM is not subject to any restrictions for the selection of brazing alloy. Commonly used brazing filler metal types such as BCup Alloy (may contain 0%-30% Silver – Ag) or Bag Alloy (may contain anywhere between 24% and 93% Silver – Ag) can be used. The brazing alloy chosen must be clarified with the brazing alloy supplier for each specific application. The selection of brazing alloy may depend on a few factors: applicable codes, OEM specifications, vibration, and operating temperatures.

¹ Streamline® XHPTM Copper Fittings shall be made from material in compliance with UNS C19400 grade of copper.