

## Mueller Streamline Co. Headquarters

150 Schilling Blvd Suite 201

Collierville, Tennessee 38017

**United States** 

Phone: 901 753 3200

### Mueller Streamline Co. International

525 Okeechobee Blvd

Suite 860

West Palm Beach, FL 33401

**United States** 

Phone: 561 273 8300

# ITEM # X 04004, REDUCING TEE, C X C X C, 1/2" X 3/8" X 3/8"

Streamline® XHP<sup>TM</sup> Copper-Iron Fittings for use in refrigeration applications. Available sizes ranging from 3/8" to 2-1/8" for continuous 130 BAR / 1885 PSI pressure ratings at 120°C / 250°F.



### <u>Specifications</u> | <u>Dimensions</u> | <u>Details</u>

Specifications –				
	Weight	0.04 lb		
	Material <sup>1</sup>	COPPER-IRON		
	Operating Temperature [Max]	250 °F		
	Operating Pressure [Max]	1885 psi		
	End Type	Cup (Braze)		
	End Size	1/2 in		

Second End Type	Cup (Braze)
Second End Size	3/8 in
Third End Type	Cup (Braze)
Third End Size	3/8 in
Standards	Copper-iron (CuFe2P) UNS C19400 130 BAR / 1,885 PSI 120°C / 250°F

Dimensions –				
0	Overall Length	1.39 in		
0	overall Height	0.91 in		
0	Overall Width	0.58 in		
Х		0.24 in		
X	1	0.43 in		
Y		0.31 in		

Details ————————————————————————————————————				
	Qty Pcs / Bag	5		
	Master Qty Pcs / Box	100		
	Mueller Description	1/2 X 3/8 X 3/8 OD TEE		
	Key Specifications	Streamline® XHP <sup>TM</sup> Copper Fittings is third party verified through Underwriters Laboratories for max operating temperature of 250° F (120° C) and continuous operating pressure of 1740 psi (120 Bar).		
		Streamline® XHP <sup>TM</sup> copper material was developed for use with high pressure refrigerants. Compared to conventional pure copper Cu-DHP (99.9% Cu; UNS C12200), Streamline® XHP <sup>TM</sup> material is a CuFe2P alloy (2% iron; UNS C19400). This material's wettability is		

#### Installation

comparable to that of Cu-DHP. Streamline® XHP<sup>TM</sup> is not subject to any restrictions for the selection of brazing alloy. Commonly used brazing filler metal types such as BCup Alloy (may contain 0%-30% Silver – Ag) or Bag Alloy (may contain anywhere between 24% and 93% Silver – Ag) can be used. The brazing alloy chosen must be clarified with the brazing alloy supplier for each specific application. The selection of brazing alloy may depend on a few factors: applicable codes, OEM specifications, vibration, and operating temperatures.

<sup>&</sup>lt;sup>1</sup> Streamline® XHP<sup>TM</sup> Copper Fittings shall be made from material in compliance with UNS C19400 grade of copper.