

Mueller Streamline Co. Headquarters

150 Schilling Blvd Suite 201

Collierville, Tennessee 38017

United States

Phone: 901 753 3200

Mueller Streamline Co. International

525 Okeechobee Blvd

Suite 860

West Palm Beach, FL 33401

United States

Phone: 561 273 8300

ITEM # X 04070, REDUCING TEE, C X C X C, 1-3/8" X 1-3/8" X 7/8"

Streamline® XHP TM Copper-Iron Fittings for use in refrigeration applications. Available sizes ranging from 3/8" to 2-1/8" for continuous 130 BAR / 1885 PSI pressure ratings at 120°C / 250°F.



<u>Specifications | Dimensions | Details</u>

Specifications –					
	Weight	0.46 lb			
	Material ¹	COPPER-IRON			
	Operating Temperature [Max]	250 °F			
	Operating Pressure [Max]	1885 psi			
	End Type	Cup (Braze)			
	End Size	1 3/8 in			

Second End Type	Cup (Braze)
Second End Size	1 3/8 in
Third End Type	Cup (Braze)
Third End Size	7/8 in
Standards	Copper-iron (CuFe2P) UNS C19400 130 BAR / 1,885 PSI 120°C / 250°F

	Dimensions -					
Overall Length 3.00 in						
Overall Height 2.33 in						
Overall Width 1.58 in						
X 0.59 in						
X1 0.59 in						
Y 0.91 in						

De	Details			
	Qty Pcs / Bag	1		
	Master Qty Pcs / Box	60		
	Mueller Description	1-3/8X 1-3/8X 7/8OD TEE		
	Key Specifications	Streamline® XHP TM Copper Fittings is third party verified through Underwriters Laboratories for max operating temperature of 250° F (120° C) and continuous operating pressure of 1740 psi (120 Bar).		
		Streamline® XHP TM copper material was developed for use with high pressure refrigerants. Compared to conventional pure copper Cu-DHP (99.9% Cu; UNS C12200), Streamline® XHP TM material is a CuFe2P alloy (2% iron; UNS C19400). This material's wettability is		

Installation

comparable to that of Cu-DHP. Streamline® XHPTM is not subject to any restrictions for the selection of brazing alloy. Commonly used brazing filler metal types such as BCup Alloy (may contain 0%-30% Silver – Ag) or Bag Alloy (may contain anywhere between 24% and 93% Silver – Ag) can be used. The brazing alloy chosen must be clarified with the brazing alloy supplier for each specific application. The selection of brazing alloy may depend on a few factors: applicable codes, OEM specifications, vibration, and operating temperatures.

¹ Streamline® XHPTM Copper Fittings shall be made from material in compliance with UNS C19400 grade of copper.