



Technical Data Sheet

Maximum Temperature Thread Sealant

INDUSTRIAL

PRODUCT DESCRIPTION

S.I.N.: 834-300

Permatex® Maximum Temperature Thread Sealant with PTFE is formulated for fast, responsive curing on metal pipe threads and fittings. This sealant is a smooth, white paste-like compound that controls lubricity to assist assembly and torque tightening. Permatex® Maximum Temperature Thread Sealant replaces Teflon® tape or pipe dopes. It cures rapidly to withstand 10,000 PSI within 24 hours. Prevents galling and protects mated threaded surfaces from rust and corrosion. The product cures when confined in the absence of air between close fitting metal surfaces. This product may not be compatible with some thermoplastic materials.

PRODUCT BENEFITS

- Quick fixture time
- Prevents galling and corrosion
- Controlled strength
- Temperature and solvent resistance
- Immediate low pressure sealing
- Contains PTFE

TYPICAL APPLICATIONS

Recommended for sealing metal tapered pipe threads and fittings up to 5cm (2 inches) National Pipe Thread (NPT) for industrial applications in the chemical processing, petroleum refining, pulp/paper, waste treatment, textile, utilities/power generation, marine, automotive, industrial equipment, gas compression and distribution industries. It is also recommended for industrial plant fluid power systems.

- Stainless steel fittings
- Head bolts into through holes
- Oil PSI sending units/sensors
- Fuel fittings
- Oil and coolant lines
- Hydraulic line fittings
- Brake fittings
- Transmission fluid fittings
- PTO fittings
- Air conditioning fittings

DIRECTIONS FOR USE

1. For best performance, surfaces should be clean and free of grease.
2. Product should be applied to the thread engagement area in sufficient quantity to fill all engaged threads.
3. Use accepted trade practices to assemble and wrench-tighten fittings until proper alignment is obtained.

4. This product performs best in thin bond gaps (0.05mm).
5. Very large thread sizes may create large gaps that will affect cure speed and strength.
6. For maximum pressure and solvent resistance, allow at least 24 hours for the product to fully cure before filling and pressurizing system.
7. This product is designed to give controlled friction (torque/tension ratio) during assembly.

PHYSICAL PROPERTIES OF UNCURED MATERIAL


	Typical Value
Chemical Type	Methacrylate ester
Appearance	White opaque paste
Odor	Acrid
Specific Gravity	1.10
Viscosity (cP)	300,000
Flash Point (T.C.C.) °F	>200
Chemical resistance	Gasoline, oil, water, glycol, hydraulic fluid, freon

TYPICAL CURING PERFORMANCE

Cure speed vs. substrate

The rate of cure will depend on the material used. Permatex® Maximum Temperature Thread Sealant will react faster and stronger with **Active Metals**. However, **Inactive Metals** will require the use of an activator (Surface Prep) to obtain maximum strength and cure speed at room temperature.

The graph below shows the breakaway strength developed with time on 1/2" NPT fittings compared to different materials.



NOT FOR PRODUCT SPECIFICATIONS.

THE TECHNICAL DATA CONTAINED HEREIN ARE INTENDED AS REFERENCE ONLY.


PLEASE CONTACT PERMATEx, INC., TECHNICAL SERVICE DEPARTMENT FOR ASSISTANCE AND RECOMMENDATIONS FOR YOUR SPECIFIC APPLICATION.
PERMATEx, INC., HARTFORD SQUARE NORTH, 10 COLUMBUS BOULEVARD, HARTFORD, CT 06106 PHONE - (1-87)PERMATEx

Cure speed vs. temperature

The rate of cure will depend on the ambient temperature. **Full cure** is attainable in 24 hours at room temperature, 22°C (72°F), or 1 hour at 93°C (200°F).

Cure speed vs. activator

Where cure speed is unacceptably long, or large gaps are present, applying an activator (Surface Prep) to the surface will improve cure speed. The graph below shows the shear strength developed with time on 1/2" NPT fittings using Permatex® Surface Prep Activator.



CURED INFORMATION

(3/8 NPT, Cured 24 hours @ 75°F)

Pressure Resistance (psi)	10,000
Temperature Range (°F)	-65 to +400
Breakaway torque, ISO 10964 (in.-lb.)	40
Maximum recommended pipe size*	2" NPT

* May be used on threads larger than 2" but all threads must be activated with Surface Prep Activator and the time for full cure extended to 48 hours (pipe burst pressure after 96 hours). Heat may be required for removal.

Chemical / Solvent Resistance

Aged under conditions and tested at 22°C(72°F)

% Initial Strength retained after time	Temp	500hr	1000hr
Heat aged	150°C		110%
Motor oil(SL)	125°C		110%
Antifreeze	87°C	80%	
Gasoline	23°C	65%	
IPA	23°C	25%	
Distilled water	23°C	85%	

GENERAL INFORMATION

This product is not recommended for use in pure oxygen and/or oxygen rich systems and should not be selected as a sealant for chlorine or other strong oxidizing materials.

For safe handling information on this product, consult the Material Safety Data Sheet, (MSDS).

ORDERING INFORMATION

Part Number	Container Size
56750	50 ml. tube, carded
56725	250 ml. Tube
56701	1 liter bottle

STORAGE

Products shall be ideally stored in a cool, dry location in unopened containers at a temperature between 8°C to 28°C (46°F to 82°F) unless otherwise labeled. Optimal storage is at the lower half of this temperature range. To prevent contamination of unused product, do not return any material to its original container.

NOTE

The data contained herein are furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others over whose methods we have no control. **Permatex, Inc. specifically disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose, arising from sale or use of Permatex, Inc. products and disclaims any liability for consequential or incidental damages of any kind, including lost profits.** This product may be covered by one or more United States or foreign patents or patent applications

Distributed by:

All-Spec Industries	800-537-0351 (phone)
Wilmington, NC	800-379-9903 (fax)
www.all-spec.com	sales@all-spec.com