

# LOCTITE<sup>®</sup> PC 9599<sup>™</sup>

Known as LOCTITE<sup>®</sup> Nordbak<sup>®</sup> Fast Cure Wearing Compound<sup>™</sup>  
November 2015

## PRODUCT DESCRIPTION

LOCTITE<sup>®</sup> PC 9599<sup>™</sup> provides the following product characteristics:

<b>Technology</b>	Epoxy
<b>Chemical Type</b>	Epoxy
<b>Appearance (uncured)</b>	Thixotropic blue paste
<b>Components</b>	Two component - requires mixing
<b>Mix Ratio, by weight - Resin : Hardener</b>	2 : 1
<b>Mix Ratio, by volume - Resin : Hardener</b>	2 : 1
<b>Cure</b>	Room temperature cure
<b>Application</b>	Abrasion resistance
<b>Specific Benefit</b>	<ul style="list-style-type: none"> <li>• Fast cure -renews worn surfaces fast, reduces downtime to put equipment back in service quickly</li> <li>• Easy to mix and use</li> <li>• Non-sag paste - allows application versatility for overhead and vertical surfaces</li> <li>• Non-shrinking</li> <li>• Extends wear life - resists sliding abrasive wear and eliminates costly wear part inventory</li> <li>• Can be re-applied to itself</li> </ul>

LOCTITE<sup>®</sup> PC 9599<sup>™</sup> works in less than half the time of conventional curing epoxies to rebuild, repair, and protect processing equipment from hard sliding abrasion. Like standard Nordbak<sup>®</sup> Wearing Compound<sup>™</sup>, this fast curing version is a two-component, ceramic-bead filled repair material for rebuilding and protecting chutes, pumps, elbows, cyclones and other material handling equipment against wear and abrasion under typical dry service temperatures of -30 °C to +105 °C. Other typical applications include the repair and protection of fan blades and housings, scrubbers, dust collectors and exhausters.

## TYPICAL PROPERTIES OF UNCURED MATERIAL

Coverage 0.2 m<sup>2</sup> @ 6 mm thick/2.5 kg  
(2.3 ft<sup>2</sup> @ 0.25 inch thick/6 lb)

## TYPICAL CURING PERFORMANCE

### Curing Properties

Gel Time @ 25 °C, minutes 10 to 15  
Cure Time @ 25 °C, hours 3

## TYPICAL PROPERTIES OF CURED MATERIAL

### Physical Properties:

Coefficient of Thermal Conductivity ASTM F 433, W/(m·K) 1.1  
Glass Transition Temperature ISO 11359-2, °C 58  
Coefficient of Thermal Expansion, ISO 11359-2, K<sup>-1</sup>:  
Below Tg 23  
Above Tg 100  
Compressive Strength, ISO 604 N/mm<sup>2</sup> 84  
(psi) (12,150)  
Compressive Modulus, ISO 604 N/mm<sup>2</sup> 7,035  
(psi) (1,020,300)  
Flexural strength, ASTM D790 N/mm<sup>2</sup> 49  
(psi) (7,150)  
Flexural modulus, ASTM D790 N/mm<sup>2</sup> 4,875  
(psi) (706,550)

### Electrical Properties:


Volume Resistivity, IEC 60093, ohm-cm 47×10<sup>12</sup>  
Surface Resistivity, IEC 60093, ohms 11.6×10<sup>12</sup>

## TYPICAL PERFORMANCE OF CURED MATERIAL


Lap Shear Strength, ISO 4587:  
Grit Blasted Mild Steel (GBMS) N/mm<sup>2</sup> 4.0  
(psi) (580)

**TYPICAL ENVIRONMENTAL RESISTANCE**

Lap Shear Strength, ISO 4587:  
Grit Blasted Mild Steel (GBMS)

**Hot Strength****Heat Aging**

Aged at temperature indicated and tested @ 22 °C

**GENERAL INFORMATION**

This product is not recommended for use in pure oxygen and/or oxygen rich systems and should not be selected as a sealant for chlorine or other strong oxidizing materials.

For safe handling information on this product, consult the Safety Data Sheet (SDS).

**Directions for use:****Surface Preparation**

Proper surface preparation is critical to the long-term performance of this product. The exact requirements vary with the severity of the application, expected service life, and initial substrate conditions.

1. On vertical or overhead areas, it is recommended to tack expanded metal mesh to substrate before application of LOCTITE® PC 9599™.
2. Clean, dry and abrade application surface. The more thorough the degree of surface preparation the better the performance of the application. If possible, it is recommended that the surface be grit blasted to a Near White Metal (SSPC-SP10/NACE No. 2) Standard. For less severe applications roughening the surface with

hand tools is suitable.

3. Solvent cleaning with a residue-free solvent is recommended as the final step to aid in adhesion.

**Mixing:**

1. Measure 2 parts resin to 1 parts hardener by volume or weight.
2. Transfer measured quantities or entire kit onto a clean and dry mixing surface and mix together with a trowel until uniform in color.
3. If mixing larger quantities, a spiral mixing blade attached to a high torque electric or pneumatic drill can be used.
4. If resin and hardener temperatures are 15 °C or below, preheat resin only to about 32 °C but not to exceed 38 °C.

**Application Method:**

1. Apply fully mixed material to the prepared surface .
2. With gloved hand, take a 25mm (1in) ball of mixed material and rub the surface to apply a scratch coat. By wetting out the surface, it ensures the best possible surface contact and avoids air entrapment.
3. Build up to desired thickness (minimum 6 mm), avoid air entrapment.
4. At 25 °C the working time is 10 minutes. Working and cure time depend on temperature and mass - the higher the temperature and the larger the mass, the faster the cure.
5. If a smooth surface is desired, apply a small amount of acetone or isopropyl alcohol to the compound and smooth using either a gloved hand or trowel, as the solvent prevents sticking. Do not use water as it produces a white film on the finished surface.

**Caution:** Use approved, positive-pressure, supplied-air respirator when welding or torch cutting near cured compound. Use approved self-contained breathing apparatus when burning, welding, or torch cutting indoors near cured compound. Use approved respirator for dusts and mists when grinding or machining cured compound. **DO NOT** use open flame on compound. See other cautions on Material Safety Data Sheet.

**Technical Tips for Working With Epoxies**

Working time and cure depends on temperature and mass:

- The higher the temperature, the faster the cure.
- The larger the mass of material, the faster the cure.

To speed the cure of epoxies at low temperatures:

- Store epoxy at room temperature.
- Pre-heat repair surface until warm to the touch.

To slow the cure of epoxies at high temperatures:

- Mix epoxy in small masses to prevent rapid curing.
- Cool resin/hardener component(s).

**Not for product specifications**

The technical data contained herein are intended as reference only. Please contact your local quality department for assistance and recommendations on specifications for this product.

**Storage**

Store product in the unopened container in a dry location. Material removed from containers may be contaminated during use. Do not return liquid to original container. Storage information may be indicated on the product container labeling.

**Optimal Storage: 8 °C to 21 °C. Storage below 8 °C or greater than 28 °C can adversely affect product properties.**

Henkel cannot assume responsibility for product which has been contaminated or stored under conditions other than those recommended. If additional information is required, please contact your local Technical Service Center or Customer Service Representative.

**Conversions**

$(^{\circ}\text{C} \times 1.8) + 32 = ^{\circ}\text{F}$   
 $\text{kV/mm} \times 25.4 = \text{V/mil}$   
 $\text{mm} / 25.4 = \text{inches}$   
 $\mu\text{m} / 25.4 = \text{mil}$   
 $\text{N} \times 0.225 = \text{lb}$   
 $\text{N/mm} \times 5.71 = \text{lb/in}$   
 $\text{N/mm}^2 \times 145 = \text{psi}$   
 $\text{MPa} \times 145 = \text{psi}$   
 $\text{N}\cdot\text{m} \times 8.851 = \text{lb}\cdot\text{in}$   
 $\text{N}\cdot\text{m} \times 0.738 = \text{lb}\cdot\text{ft}$   
 $\text{N}\cdot\text{mm} \times 0.142 = \text{oz}\cdot\text{in}$   
 $\text{mPa}\cdot\text{s} = \text{cP}$

**Note:**

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. The product can have a variety of different applications as well as differing application and working conditions in your environment that are beyond our control. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product.

Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

**In case products are delivered by Henkel Belgium NV, Henkel Electronic Materials NV, Henkel Nederland BV, Henkel Technologies France SAS and Henkel France SA please additionally note the following:**

In case Henkel would be nevertheless held liable, on whatever legal ground, Henkel's liability will in no event exceed the amount of the concerned delivery.

**In case products are delivered by Henkel Colombiana, S.A.S. the following disclaimer is applicable:**

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product.

Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

**In case products are delivered by Henkel Corporation, Resin Technology Group, Inc., or Henkel Canada Corporation, the following disclaimer is applicable:**

The data contained herein are furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others over whose methods we have no control. It is the user's responsibility to determine suitability for the user's purpose of any production methods mentioned herein and to adopt such precautions as may be advisable for the protection of property and of persons against any hazards that may be involved in the handling and use thereof. In light of the foregoing, **Henkel Corporation specifically disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose, arising from sale or use of Henkel Corporation's products. Henkel Corporation specifically disclaims any liability for consequential or incidental damages of any kind,**

**including lost profits.** The discussion herein of various processes or compositions is not to be interpreted as representation that they are free from domination of patents owned by others or as a license under any Henkel Corporation patents that may cover such processes or compositions. We recommend that each prospective user test his proposed application before repetitive use, using this data as a guide. This product may be covered by one or more United States or foreign patents or patent applications.

**Trademark usage**

Except as otherwise noted, all trademarks in this document are trademarks of Henkel Corporation in the U.S. and elsewhere. ® denotes a trademark registered in the U.S. Patent and Trademark Office.

## Reference 0.2