

# CHESTERTON® 124 PRODUCT DATA SHEET

## 1.0 COMPOSITION

124 is a rubber sheet which is comprised of a combination of Styrene Butadiene Rubber (SBR), Neoprene Rubber (CR), and Nitrile Rubber (NBR).

## 2.0 USAGE

This material is moderately oil and ozone resistant which can also be used against water and low pressure steam to 190°F (88°C).

## 3.0 TYPICAL PROPERTIES

- A. Width – 36” (90cm)
- B. Thickness, Inches – 1/16, 1/8, 3/16, 1/4
- C. Tensile Strength, PSI (Bar) – 800 (55)
- D. Durometer, Shore A – 55 - 65
- E. Elongation, % - 300 minimum
- F. Specific Gravity, Typical – 1.41 g/cc
- G. Pressure Rating, max., 1/8” (3.2mm) thk - 150PSI (10Bar)
- H. Oil Resistance – moderate
- I. Color – Black

---

### A.W.CHESTERTON CO.

860 Salem Street  
Groveland, MA 01834 USA  
Telephone: 781-438-7000  
Fax: 978-469-6528  
[www.chesterton.com](http://www.chesterton.com)

©A.W.Chesterton Company,2007. All rights reserved.  
®Registered trademark owned and licensed by  
A.W.Chesterton Company in USA and other countries.

FORM NO. E72027

PRINTED IN USA 02/08